

## Flame, Smoke & Toxicity

Meets or exceeds the following:	<ul style="list-style-type: none"><li>● BIFMA - Class A</li><li>● Boston Fire Dept IX 1</li><li>● Cal Tech 117-2013 Sec 1</li><li>● FAR 25.853a &amp; Appx F Part 1 (a)(1)(ii)</li><li>● FMVSS-302</li><li>● IMO Part 8 Upholstered Furniture 3.1 Smoldering Cigarette</li><li>● IMO Part 8 Upholstered Furniture 3.2 Propane Flame</li><li>● NFPA 260</li><li>● NFPA 701 Small Scale</li><li>● NY/NJ Port of Authority</li><li>● UFAC Fabric, Class 1</li><li>● Fed Std CID A-A-2950</li></ul>
---------------------------------	---

## Performance Features

Special Performance	Silverguard Anti-Microbial Agent
Use	Indoor/Outdoor
QUV hours (minimum)	650
Adhesion #/in., min (CFFA-3)	3 Warp, 3 Fill
Tensile Strength #, min (CFFA-14)	110 Warp, 85 Fill
Tack Strength #, min (CFFA-14)	60 Warp, 30 Fill
Trap Tear Strength #, min (CFFA-16c)	25 Warp, 25 Fill
Wyzeenbeek Abrasion (CFFA-1a)	60,000 Wirescreen (double rubs)
Blocking (CFFA-4 No. 1)	Pass
W-Flex - 25,000 cycles (CFFA-10)	Pass
Crocking Resistance - 20 cycles no stain (CFFA-7)	Pass
Fungal Resistance (ASTM-G-21)	Pass
Bacterial Resistance (AATCC 147)	Pass
Bacterial Resistance (AATCC 100)	Pass
Cold Crack (CFFA-6a)	-20 °F [-29 °C]
Compatible with Disinfectants	Yes. See Chem Resistance Tech Bulletin for more information.
Bleach-Safe	Yes, 10% Bleach Solution